

# SHENZHEN LANHU BATTERY CO., LTD.

MESSRS	
BRAND	<b>LANHU BATTERY OR OEM</b>
PRODUCT	3.0V LITHIUM-MANGANESE BUTTON CELL
MODEL	CR2032
PREPARED BY	JIEXIONG LI
APPROVED BY	CHICHENG ZHANG
DATE	2020/4/15

## 1、【SCOPE】

This specification applies to the following 3.0v lithium button cell CR2032 made by **SHENZHEN LANHU BATTERY CO., LTD.**

## 2. RATINGS

TABLE I :

ITEM		UNIT	SPECIFICATIONS	CONDITIONS
Nominal voltage		V	3.0	
Nominal capacity		mAh	240	Standard discharge with load 15kΩ
Instantaneous short-circuit current		mA	≥300	Time≤0.5 second
Off-load voltage		V	≥3.20	
Operating temperature		℃	-20~60	
Standard weight		g	3.1	Unit cell
Service output	Initial	Max Standard	1240 h 1200 h	Continuous discharge with load 15kΩ, till 2.0v end-voltage at 20~25℃
	After 12 months storage	Standard	1120 h	

TABLE II :

ITEM	CONDITIONS	CHARACTERISTICS	
Thermal durability	Kept for 20 days at 60℃ ±3℃ , then continuously discharge with 15kΩ load till 2.0v end-voltage	Standard	1200h
Self-discharge rate	Stored for 12 months at normal temperature and humidity	≤5%	

## 3. [PERFORMANCE AND TEST METHODS]

Unless otherwise stated, all the testing is carried out under the condition: environmental temperature, 20℃~25℃; environmental humidity, 65±20%. Please refer to TableIII

## 4. [SUGGESTIONS AND CAUTIONS]

- 4.1 Install batteries correctly.
- 4.2 Ensure the contact points to be clean and conductive.
- 4.3 Do not mix different types, different brands batteries to serve together.
- 4.4 Do not heat, recharge the batteries.
- 4.5 Do not dispose of the batteries in fire.
- 4.6 Keep away from the small children, if swallowed promptly see doctor.
- 4.7 Pay attention to the producing date.


TABLE III:

No	ITEM	TEST METHODS	STANDARD	
1	Dimensions	Using vernier caliper (accuracy $\geq 0.02$ ) while avoiding short-circuit	Diameter	20.0 (-0.20) mm
			Height	3.2 (+0.20) mm
2	Off-load voltage	Using multimeter (accuracy $\geq 0.25\%$ ) internal resistance $\geq 1M\Omega$	$\geq 3.20$ V	
3	Instantaneous short-circuit current	Time of short-circuit should be less than 0.5 second and avoid repeated test within half an hour	$\geq 300$ mA	
4	Appearance	Eyeballing	Bright, clean, no rust, no leakage, And no flaw	
5	Capacity	Continuously discharge for 8 hours with load 15k $\Omega$ , temperature at 20~25 $^{\circ}$ C, humidity at 65 $\pm$ 20% till 2.0v end-voltage (for fresh battery only: within 3 months )	$\geq 1200$ h	
6	Vibration test	Put battery on the platform of the vibrations machine, start the machine and adjust the frequency form 10 times per minute to 15 times per minute. keep it running for an hour	Characteristics keep stability	
7	Leakage at high temperature test	Stored under temperature (60 $^{\circ}$ C) for 7 days	No leakage allowed	
8	Over discharge Test	After 2.0v end-voltage, continuously discharged for 5 hours	No leakage allowed	

## 5. 【CUTAWAY DIAGRAM OF 3.0V LITHIUM MANGANESE DIOXIDE BUTTON CELL】

3.0V 锂—二氧化锰扣式电池剖面图

Cutaway Diagram of 3.0V Lithium Manganese Dioxide Button Cell



- |                             |                              |               |          |
|-----------------------------|------------------------------|---------------|----------|
| 1、负极壳                       | 2、负极锂片                       | 3、隔膜          | 4、密封胶圈   |
| 5、正极片                       | 6、正极集流网                      | 7、正极壳         |          |
| 1、Cathode Shell             | 2、Cathode (slice of lithium) | 3、Septum      | 4、Gasket |
| 5、Anode (MnO <sub>2</sub> ) | 6、Anode collector net        | 7、Anode shell |          |

## 6. 【DISCHARGE CHARACTERISTICS

### 标准曲线 STANDARD CHARACTERISTICS

#### 💡 负载放电特性 Discharge Characteristics on Load



#### 🌡️ 温度放电特性 Discharge Characteristics on Temperature

